

Product Name :

Total (Green) Petroleum Coke (R.P.C)

- Result of chemical Analysis Test Turkmenistan

No	Item	Method	Test Result
1	Mass portion of the total moisture,%, not more than	ASTM D 3173-11	3 ~ 8
2	Mass portion of flying substances,%, not more than	INSO 11098-1390	8 ~ 11
3	Mass portion of sulfur, in%, not more than	ASTM E1915-13	0.9 ± 0.2
4	Ash content,%, not more than	ASTM D3174-12	1~ 2
5	Fixed Carbon	ASTM D3175-12	89 ~ 92 %
6	Mass portion of coke with the size of pieces not less than 8 mm,%, not more than	-----	60
7	Real density after warming up at 1300° C in a current of 5 hours/sm ³ , not less than 2,0	-----	2,06 - 2,08

Note: The position is not rejection and defined for calculation with consumer.

Exir Faraz Sadid