

No:

Date:

Product Name :

Calcined Petroleum Coke (C.P.C)

- Result of chemical Analysis Test

No	Item	Method	Test Result
1	Total Moisture Content (W.W)	ASTM D 3173-11	< 0.8 %
2	Volatile Matter (Air dried)	INSO 11098-1390	< 1.2 ~ 1.5 %
3	Total Sulphur, not more than	ASTM E1915-13	0.9 ± 0.2 %
4	Ash Content	ASTM D3174-12	< 0.5 ~ 1 %
5	Fixed Carbon	ASTM D3175-12	95 - 98.5 %
6	Absorbency content	-----	92%
7	Mass portion of oiled	-----	< 0.5 %
8	Real Density , g/ sm ³	-----	2,06 - 2,08

Note:

- Sizing of our products are as following :
- Bulk Size for Aluminyum industry.
 - 1- Size 0 – 1 mm for injection.
 - 2- Size 1 – 3 for steel & metal.
 - 3- Size 1 – 5 Cast iron.
 - 4- Size 3 – 8 by the order of client.

Exir Faraz Sadid

